



experience,
trust, service

800-BLAST-IT
www.marcousa.com

D a v e n p o r t , I A • H o u s t o n , T X • S a v a n n a h , G A • H a r r i s b u r g , P A

Autofax #00093797

Updated: 04/19/05

BLASTING DATA GUIDE

Surface Condition	Square Foot Per Hour by Nozzle Size				
-------------------	-------------------------------------	--	--	--	--

White Metal	#8	#7	#6	#5	#4
Loose Mill Scale	250	200	145	102	61
Tight Mill Scale	211	164	121	84	50
Pitted Paint	125	100	71	50	32
Multicoats	100	80	58	40	25

Near White Metal	#8	#7	#6	#5	#4
Loose Mill Scale	265	210	150	106	65
Tight Mill Scale	220	172	125	90	55
Pitted Paint	132	104	75	55	34
Multicoats	106	84	60	44	25

Commercial	#8	#7	#6	#5	#4
Loose Mill Scale	632	495	360	255	155
Tight Mill Scale	420	320	240	170	102
Pitted Paint	316	246	181	128	76
Multicoats	210	165	120	85	50

Brush Off	#8	#7	#6	#5	#4
Loose Mill Scale	1264	990	720	508	310
Tight Mill Scale	1264	990	720	508	310
Pitted Paint	1264	990	720	508	310
Multicoats	1264	990	720	508	310

Information provided on this chart is approximate and to be used as a general guide to determine square footage per hour based on different nozzle orifice size(s) and different surface condition results.

